

Diamond Plate Runner Mats

Specification Sheet



| Uses | Heavily trafficked indoor areas |
|--|--------------------------------------|
| Colors | Black; Gray; Black w/ Yellow Borders |
| Compound | Polyvinyl Chloride |
| Tabor Abrasion (% Lost @ 1,000 Cycles per Fed. Std. 191 | 1% lost |
| Coefficient of Friction per ASTM F1677 | 0.68 Dry, 0.17 Wet |
| Thickness | 3/16" |
| Tensile Strength | 1250 lbs. psi per ASTM D412 |
| Warranty | 1 Year |
| Green Rating | 100% Post Industrial |