

Traction Tread Rubber Runner Mats

Specification Sheet



Performance	Best
Uses	Indoor / Cover Outdoor Applications
Compound	100% Nitrile Rubber
Coefficient of Friction	0.92 Dry / 0.86 Wet per ASTM C1028-96
Tabor Abrasion	< 1% lost @ 1,000 cycles per Fed. Std. 191
Flammability	"A" Rating per MVSS 302
Warranty	1 years
Tensile Strength	1600 lbs. per sq. inch per ASTM D412
Wear Resistance	5+
Slip Resistance	5+